

## Development Data Sheet



Characteristics	Test Method	Lite	Medium
Structure		Oscillated	
Polymer		100% Recycled High density polyethylene	
Colour		Green	
Tensile strength (kN/m) [MD]	ISO 10319	6	9
Yield point elongation (%)		13	22
Residual thickness @500kPa	ASTM D1621	60	80
Slip risk PTV value (average)	BS7976: 1-3	>40 (low)	

Nominal dimensions	Lite	Medium
Width (m)	2	2
Length (m)	20	20
Thickness (mm)	10	13
Weight/m <sup>2</sup> (kg)	0.95	1.6
Weight/linear m (kg)	1.9	3.2
Roll weight (kg)	38	64